



Client:

Entry No:

Date received: 21/02/2014

Client's Description: Sample of fabric Dahlia T70 Crib 7

### TEST REPORT

Test Required: Flammability BS 7175 ignition source 7

Pre-treatment: None

Conditioning: A minimum of 72 hours at indoor ambient and then 24 hours at 65 +/- 5% Relative Humidity, 20 +/- 5°C

Method of Test: BS 7175: 1989 (2008) Section 3

Date of Test: 05/03/2014

The following test results relate only to the ignitibility of the combination of materials under the particular conditions of test: they are not intended as a means of assessing the full potential fire hazard of the bedcovers in use.

| Ignition Source | Positions                         | Observations                                                                                                                   | Result |
|-----------------|-----------------------------------|--------------------------------------------------------------------------------------------------------------------------------|--------|
| 7 (wood crib)   | (i) On Top<br>(ii) Below overhang | Flaming ceased within the specified thirteen minute period after ignition of the crib and no progressive smouldering occurred. | PASS   |

-----End of Document-----

*This is hereby certified to be a correct return of the tests made of the items referred to herein.*

Geoff Briggs C.Text., A.T.I.  
Head of laboratory  
7<sup>th</sup> March 2014



- ❖ Unless instructed otherwise by the client sample remnants will be disposed of after 28 days
- ❖ Test marked (\*) in this certificate are not included in the UKAS Accreditation Schedule for this Laboratory.
- ❖ Opinions and interpretations expressed herein are outside the scope of UKAS accreditation.
- ❖ This Certificate relates only to the sample received and, unless that sample has been drawn by the staff of this laboratory, or its agent, and endorsed accordingly, any application of the result to a bulk quantity or other material is entirely the responsibility of the client.

